

Acriflex pH4

Two-component, water-based, fibre-reinforced cementitious waterproofing (such as **Acriflex pH4**) resistant to highly acidic or basic substances. Suitable for waterproofing surfaces in contact with or containing corrosive substances. Minimum required characteristics: Water Impermeability 9.5 Atm; Break Elongation 87 %; Crack Bridging Ability 2.0 mm; Weathering Test 1680 hours (>10 years); Chemical resistance to pH between 2 and 12 – excellent; Frost and thaw resistance – unaltered after 50 cycles between -15°C a +15°C; Puncture resistance 68.7 N.

DIASEN srl

Zona Ind. Berbentina, 5 60041 Sassoferrato (AN) - ITALY
Tel. +39 0732 9718 - Fax +39 0732 971899 - diasen@diasen.com - www.diasen.com
PARTITA IVA 01553210426 - R.E.A. Ancona n.150933
Reg.Imp. Ancona 01553210426 - Cap. Soc. €400.000,00 i.v.

