

## *Decork Façade*

Coloured coating in paste (such **Decork Façade**) formulated with cork and water-based resins, ideal for finishing thermo-acoustic plaster, thermal insulation systems, old facades subject to cracks and lesions. Minimum required characteristics: Elasticity 195%; Crack Bridging Ability 2.5 mm; Spindle Resistance 2 mm; Weathering Test 1680 hours (> 10 hours); Thermal conductivity ( $\lambda$ ) 0.086 W/mK; Adhesion by direct traction on self-levelling cementitious screed 0.98–1.12 N/mm<sup>2</sup>; Theoretical specific heat 1.8 KJ/kg K; Water vapour permeability coefficient  $\mu = 15$ .

### **DIASEN srl**

Zona Ind. Berbentina, 5 60041 Sassoferrato (AN) - ITALY  
Tel. +39 0732 9718 - Fax +39 0732 971899 - diasen@diasen.com - www.diasen.com  
PARTITA IVA 01553210426 - R.E.A. Ancona n.150933  
Reg.Imp. Ancona 01553210426 - Cap. Soc. €400.000,00 i.v.

