

DIATHONITE THERMACTIVE

Cork and lime-based spray-applied thermal insulation

Natural lightweight thermal insulation based on cork (grain size 0 – 3 mm), expanded amorphous silica, perlite and pumice combined in a suitable grain size curve. Composed of natural hydraulic lime NHL 5, the product is antibacterial and prevents the formation of mould and condensation. *Diathonite Thermactive* is ready to use, has excellent fire reaction performance, high porosity, breathability and is recyclable as aggregate at the end of its life. The thermal insulation isolates from cold and heat, contributes to the hygrometric comfort in indoor environments and maintains its characteristics over time.

YIELD

2.60 kg/m² (±20%) per cm of thickness.

1.35 lb/ft² (±20%) per inch of thickness.

PACKAGING

15 kg (33.07 lb) paper bag.

Pallet: n° 60 paper bags (900 kg – 1984 lb).

APPEARANCE AND COLOR

Powder

Light Grey

STORAGE

Store the product in its original, tightly closed packaging, appropriately protected from direct sunlight, water, and frost, at temperatures between +5°C and +35°C. Shelf life: 12 months.

FIELDS OF APPLICATION

Lightweight natural thermal insulation coat for indoor and outdoor applications, suitable for thermal insulation and dehumidification. It solves problems related to thermal bridges and moisture-induced mould, ensuring a healthy environment and high living comfort. Furthermore, *Diathonite Thermactive* is a

natural compound and is suitable where eco-friendly materials are required.

BENEFITS

- Insulates against cold and heat.
- High breathability.
- Lightweight.
- Prevents mould and condensation.
- Stable and durable system over time.
- High porosity.
- Absorbs and releases excess moisture.
- Ideal for historical restoration.
- Preserves the masonry over time.
- Fast construction system (thermal brick + thermal plaster).
- Applicable over old plasters.
- Fireproof.
- Seamless system.
- Double CE marking (EN 998-1, EN 998-2).

PREPARATION OF THE SUPPORT

The substrate must be completely cured and have sufficient resistance. The surface must be thoroughly cleaned, dry, well-consolidated, free from crumbly and inconsistent parts, and perfectly levelled. Any cracks, discontinuities, or degraded portions must be restored beforehand. Before application, protect all elements that are not to be affected by the coating.



DIASEN

DIASEN SRL UNIPERSONALE – Società Benefit
Zona Industriale Berbentina 5 – 60041 Sassoferrato (AN) | Italy
+39 07329718 | diasen.com | P.IVA 01553210426
R.E.A. Ancona n. 150933 Reg. Imp. Ancona 01553210426
Cap. Soc. € 400.000,00 i.v.

The indications and requirements reported, although representing our best experience and knowledge, are to be considered indicative and must be confirmed by exhaustive practical applications. Diasen does not know the specificities of the processing and even less the determining characteristics of the application support. Therefore, before using the product, the applicator must in any case carry out preliminary tests, aimed at verifying the perfect suitability for the intended use and, in any case, assumes all responsibility that may derive from its use. In case of uncertainty and doubts, contact the company's technical office before starting the work, it being understood that such support constitutes a simple aid for the applicator, who must in any case guarantee the possession of adequate skills and experience for the installation of the product and for identifying the most suitable solutions. Always refer to the latest updated version of the technical data sheet, available on the website www.diasen.com, which cancels and replaces any other.

DIATHONITE THERMACTIVE

Cork and lime-based spray-applied thermal insulation

For substrates not included in the technical data sheet, contact the Diasen technical office.

Bricks/Blocks

No primer is required; the application can be carried out directly on the thermal brick substrate.

Concrete

In the presence of damaged and crumbly concrete, proceed with the restoration using a suitable cement-based repair mortar. Any exposed reinforcement bars must be pre-treated with specific passivating and/or anti-corrosive products suitable for structural restoration.

- **Smooth Concrete:** apply *Aquabond* primer (refer to the technical data sheet).
- **Rough Concrete:** no primer is required; the application can be carried out directly on the substrate.

Cellular Concrete

No primer is required; the application can be carried out directly on the cellular concrete substrate.

Hemp-lime or hemp-concrete blocks

No primer is required; the application is possible on hemp-lime or hemp-cement blocks only if *Diathonite Thermactive* is reinforced with *Polites 140* fibreglass mesh (refer to the technical data sheet).

Masonry

If necessary, clean the surface using a high-pressure washer or by brushing. Check the condition of the masonry and restore damaged or unstable bricks or stones.

In the presence of salts, provide for the application of *Diathonite Regularization*

or, alternatively, *Diathonite Deumix+* (refer to the technical data sheets).

On substrates to be levelled, use lime-based mortars to preserve breathability, such as *Diathonite Regularization* or *Calce Storica*.

Old plaster

Ensure that the plaster is consistent and well-adhered to the substrate; otherwise, provide for its partial or total removal. In the presence of salts, provide for the removal of the damaged plaster and the application of *Diathonite Regularization* or *Diathonite Deumix+* (refer to the technical data sheets).

In the case of painted plasters, given the wide variety of paints on the market, and on smooth plasters, it is recommended to remove the paint or to perform a substrate chipping, and then apply *Aquabond* primer. On rough plasters, proceed with the direct application of *Diathonite Thermactive*. Before application, it is always necessary to verify that the existing plaster is compatible with the characteristics and composition of *Diathonite Thermactive*. In the case of gypsum-based plasters, complete removal is recommended to avoid compromising the stability of the system due to material incompatibility.

Pannels and wood

On untreated **cork** or **lime-hemp panels**, apply *Diathonite Thermactive* without a primer.

On **wood panels** (OSB, CLT, wood fiber), **fiber cement boards** (e.g., Aquapanel), and **exterior gypsum boards**, the use of *Aquabond* primer is necessary. For a professional result, ensure that the panels are tightly joined together and that the mechanical fastening is capable of supporting the weight of the plaster.

In any case, provide reinforcement with a fiberglass mesh such as *Polites 140* at half the thickness of *Diathonite Thermactive*.

DIASEN

DIASEN SRL UNIPERSONALE – Società Benefit
Zona Industriale Berbentina 5 – 60041 Sassoferrato (AN) | Italy
+39 07329718 | diasen.com | P.IVA 01553210426
R.E.A. Ancona n. 150933 Reg. Imp. Ancona 01553210426
Cap. Soc. € 400.000,00 i.v.

The indications and requirements reported, although representing our best experience and knowledge, are to be considered indicative and must be confirmed by exhaustive practical applications. Diasen does not know the specificities of the processing and even less the determining characteristics of the application support. Therefore, before using the product, the applicator must in any case carry out preliminary tests, aimed at verifying the perfect suitability for the intended use and, in any case, assumes all responsibility that may derive from its use. In case of uncertainty and doubts, contact the company's technical office before starting the work, it being understood that such support constitutes a simple aid for the applicator, who must in any case guarantee the possession of adequate skills and experience for the installation of the product and for identifying the most suitable solutions. Always refer to the latest updated version of the technical data sheet, available on the website www.diasen.com, which cancels and replaces any other.

DIATHONITE THERMACTIVE

Cork and lime-based spray-applied thermal insulation

APPLICATION BY PLASTERING MACHINE

Suggested plastering machines

The indicated plastering machines represent only some of the models available on the market. Other models with equivalent characteristics and performances can be used. All recommended models use screw or rotary systems, but the speed, mixer size, and screw geometry differ. Therefore, the consistency and flow of the plaster may require minor adjustments to the water/material ratio to achieve optimal results.

- PFT G4
- PFT Ritmo XL
- Imer Koine 4
- Turbosol Giotto 4
- Putzmeister MP 25

In the case of application with the aforementioned *three-phases* plastering machines, the ideal equipment includes the installation of a new **D6-3 stator/rotor (screw pump)** and a **closed shafts mixer**. The setup must be completed with a tapered hose (**Ø 35/25 mm**) and a **14 or 16 mm** nozzle to ensure the correct projection of the product.

- PFT G5

In the case of application with the aforementioned plastering machine, the ideal equipment includes the installation of a **D6 – 2L stator/rotor (screw pump)** and a **closed shafts mixer**. The setup must be completed with a **tapered hose** (length 150 mm, Ø 35/25 mm) and a **16 mm nozzle** to ensure the correct projection.

- Putzmeister SP 11 LMR

For this diesel plastering machine, the setup must include a **2L6 screw pump (stator/rotor)**, a **250 mm** long hose with a **35 mm diameter**, and a **spray gun** with a **16 mm** nozzle.

Mixing

Load the content of the bags into the hopper. Adjust the machine flow meter first to **400-600 L/h** to moisten the hose, then to **150-250 L/h** for regular application. The mixture must appear as a **light and foamy mass**, characterized by a widespread and homogeneous micro-alveolar structure, and must be *matte* (free from shine). To avoid altering the chemical-physical balance of the compound, the addition of any foreign product is strictly prohibited. Depending on the water absorption rate of the substrate and the environmental conditions, it is recommended to dose the correct amount of water necessary to achieve proper adhesion.

The specified water quantity is indicative.

Application

1. It is essential to moisten the substrate, especially during the summer period and on masonry exposed to the sun. If the surface has already been primed, proceed directly with the application.
2. Create reference points or screed strips to achieve the required thicknesses. Points or strips can be made using *Diathonite Thermactive* or with aluminium or wooden profiles. In the latter two cases, the strips must be removed immediately after applying the last layer of plaster and filled with *Diathonite Thermactive*.
3. Corner profiles (made of PVC, stainless steel, or CMP | in any case lime-resistant) can be positioned together with the screed strips, but must always be placed before applying the final coat.
4. Corner profiles (made of PVC, stainless steel, or CMP | in any case lime-resistant) can be positioned together with the screed strips, but must always be placed before applying the final coat.

DIASEN

DIASEN SRL UNIPERSONALE – Società Benefit
Zona Industriale Berbentina 5 – 60041 Sassoferrato (AN) | Italy
+39 07329718 | diasen.com | P.IVA 01553210426
R.E.A. Ancona n. 150933 Reg. Imp. Ancona 01553210426
Cap. Soc. € 400.000,00 i.v.

The indications and requirements reported, although representing our best experience and knowledge, are to be considered indicative and must be confirmed by exhaustive practical applications. Diasen does not know the specificities of the processing and even less the determining characteristics of the application support. Therefore, before using the product, the applicator must in any case carry out preliminary tests, aimed at verifying the perfect suitability for the intended use and, in any case, assumes all responsibility that may derive from its use. In case of uncertainty and doubts, contact the company's technical office before starting the work, it being understood that such support constitutes a simple aid for the applicator, who must in any case guarantee the possession of adequate skills and experience for the installation of the product and for identifying the most suitable solutions. Always refer to the latest updated version of the technical data sheet, available on the website www.diasen.com, which cancels and replaces any other.

DIATHONITE THERMACTIVE

Cork and lime-based spray-applied thermal insulation

5. Moisten *Diathonite Thermactive* before the application of each coat.
6. Spray the product from bottom to top, applying a first coat of *Diathonite Thermactive*, taking care to create a thickness of **up to 40 mm**.
7. If the design thickness is not reached with the first coat, apply additional layers of *Diathonite Thermactive* only when the underlying layer is dry to the touch and visually lighter in colour (approx. 12–24 hours), maintaining a thickness of **≤ 40 mm** per coat.
8. Spray *Diathonite Thermactive* with as few interruptions as possible. Otherwise, soak the nozzle in water to prevent the formation of a clog (material plug) inside the spray gun.
9. For thicknesses **exceeding 60 mm**, it is mandatory to incorporate *Polites 140* fibreglass mesh (see technical data sheet) at approximately mid-thickness of the overall layer. Regardless of the thickness, the use of the mesh is also recommended on panels and wooden substrates, on surfaces subject to movement, on composite materials other than those mentioned, and at critical points such as doors, windows, and openings.
10. In correspondence with beams and columns, the mesh must overlap onto both sides of the concrete element by at least **150 mm**.
11. During the levelling phase, do not compress *Diathonite Thermactive* to preserve the product's porosity. Use an H-profile straight edge or a knife-edge screed, working in both horizontal and vertical directions until a regular surface is obtained.

APPLICATION BY HAND

Mixing

If mixed in a mixer or with a mixing drill, add **12–15 L** of clean water for each bag of *Diathonite Thermactive* (15 kg). Do not mix

the compound in the cement mixer for more than **3–4 minutes**. Depending on the water absorption rate of the substrate and the environmental conditions, it is recommended to dose the correct amount of water necessary to achieve proper adhesion. The specified water quantity is indicative.

Application

1. It is essential to moisten the substrate, especially during the summer period and on masonry exposed to the sun. If the surface has already been primed, proceed directly with the application.
2. Create reference points or screed strips to achieve the required thicknesses. Points or strips can be made using *Diathonite Thermactive* or with aluminium or wooden profiles. In the latter two cases, the strips must be removed immediately after applying the last layer of plaster and filled with *Diathonite Thermactive*.
3. Corner profiles (made of PVC, stainless steel, or CMP | in any case lime-resistant) can be positioned together with the screed strips, but must always be placed before applying the final coat.
4. In the case of applications on multi-storey buildings, use aluminium corner beads to secure the corners; these must be fixed with the plaster itself to avoid thermal bridges.
5. Moisten *Diathonite Thermactive* before the application of each coat.
6. Apply with a trowel a coat of *Diathonite Thermactive*, taking care to create a thickness of **up to 40 mm**.
7. If the design thickness is not reached with the first coat, apply additional layers of *Diathonite Thermactive* only when the underlying layer is dry to the touch and visually lighter in colour (approx. 12–24 hours), maintaining a thickness **of ≤ 40 mm** per coat.

DIASEN

DIASEN SRL UNIPERSONALE – Società Benefit
 Zona Industriale Berbentina 5 – 60041 Sassoferrato (AN) | Italy
 +39 07329718 | diasen.com | P.IVA 01553210426
 R.E.A. Ancona n. 150933 Reg. Imp. Ancona 01553210426
 Cap. Soc. € 400.000,00 i.v.

The indications and requirements reported, although representing our best experience and knowledge, are to be considered indicative and must be confirmed by exhaustive practical applications. Diasen does not know the specificities of the processing and even less the determining characteristics of the application support. Therefore, before using the product, the applicator must in any case carry out preliminary tests, aimed at verifying the perfect suitability for the intended use and, in any case, assumes all responsibility that may derive from its use. In case of uncertainty and doubts, contact the company's technical office before starting the work, it being understood that such support constitutes a simple aid for the applicator, who must in any case guarantee the possession of adequate skills and experience for the installation of the product and for identifying the most suitable solutions. Always refer to the latest updated version of the technical data sheet, available on the website www.diasen.com, which cancels and replaces any other.

DIATHONITE THERMACTIVE

Cork and lime-based spray-applied thermal insulation

8. For thicknesses **exceeding 60 mm**, it is mandatory to incorporate *Polites 140* fibreglass mesh at approximately mid-thickness of the overall layer. Regardless of the thickness, the use of the mesh is also recommended on panels and wooden substrates, on surfaces subject to movement, on composite materials other than those mentioned, and at critical points such as doors, windows, and openings.
9. In correspondence with beams and columns, the mesh must overlap onto both sides of the concrete element by at least 150 mm.
10. During the levelling phase, do not compress *Diathonite Thermactive* to preserve the product's porosity. Use an H-profile straight edge or a knife-edge screed, working in both horizontal and vertical directions until a regular surface is obtained.

APPLICATION FOR VENTILATED FACADE SYSTEMS

After preparing the substrate, proceed with the installation and wall-fixing of the substructure components for the ventilated façade, according to the project specifications.

1. Depending on the type of substrate, evaluate the possible need to apply *Aquabond* primer.
2. Apply *Diathonite Thermactive* the specifications mentioned in the paragraphs above (either "**Application by Plastering machine**" or "**Application by hand**") until the design thickness is reached.
3. Once the necessary drying times have elapsed, apply the *Revela Zero* water repellent (refer to technical data sheet).
4. It is recommended to pay particular attention to the points where *Diathonite Thermactive* is most subject to hygrometric stress, such

as the base of the wall near the ground or the joints between the flat roof slab and the external walls. At these points, the use of appropriate flashings and/or localized waterproofing is recommended.

5. Conclude with the installation of the cladding system (outer skin) and all other elements necessary to complete the ventilated façade according to the project specifications.

CEILING APPLICATION

For ceiling applications, *Diathonite Thermactive* must be applied using plastering machines.

1. If the surface is not primed with *Aquabond*, dampen the substrate.
2. Create screed strips to achieve the desired thickness, as specified in the previous paragraphs.
3. Apply *Diathonite Thermactive* in layers with a maximum thickness of 20 mm.
4. Embed *Polites 140* fibreglass mesh at mid-thickness of the total layer, applying it while the product is still fresh, ensuring an overlap of **150 mm** at the joints. Avoid the formation of ripples or bubbles.
5. Apply the second coat of plaster only when the underlying layer has sufficiently hardened, ensuring that the reinforcement mesh is completely embedded and without leaving any holes on the surface. On unstable substrates or for high thicknesses, it is advisable to secure the mesh with plugs or nails.
6. The screed strips must be removed when the plaster surface is compact and not damp to the touch. The voids left by the strips must be filled with *Diathonite Thermactive*.
7. During the levelling phase, do not compress *Diathonite Thermactive* to preserve the product's porosity. Use an H-profile straight edge or a

DIASEN

DIASEN SRL UNIPERSONALE – Società Benefit
Zona Industriale Berbentina 5 – 60041 Sassoferrato (AN) | Italy
+39 07329718 | diasen.com | P.IVA 01553210426
R.E.A. Ancona n. 150933 Reg. Imp. Ancona 01553210426
Cap. Soc. € 400.000,00 i.v.

The indications and requirements reported, although representing our best experience and knowledge, are to be considered indicative and must be confirmed by exhaustive practical applications. Diasen does not know the specificities of the processing and even less the determining characteristics of the application support. Therefore, before using the product, the applicator must in any case carry out preliminary tests, aimed at verifying the perfect suitability for the intended use and, in any case, assumes all responsibility that may derive from its use. In case of uncertainty and doubts, contact the company's technical office before starting the work, it being understood that such support constitutes a simple aid for the applicator, who must in any case guarantee the possession of adequate skills and experience for the installation of the product and for identifying the most suitable solutions. Always refer to the latest updated version of the technical data sheet, available on the website www.diasen.com, which cancels and replaces any other.

DIATHONITE THERMACTIVE

Cork and lime-based spray-applied thermal insulation

knife-edge screed. The product must not be trowelled or floated.

DRYING TIME

At a temperature of 23°C and a relative humidity of 50%, the product dries in 10-15 days.

- Drying times are influenced by the relative humidity of the environment and the temperature, and can vary significantly.
- When applied in high thicknesses, drying times increase significantly.
- During the curing phase, protect *Diathonite Thermactive* from frost, wind, direct sunlight, and adverse weather conditions.
- It is necessary to moisten the plaster 2-3 times a day for the first 2-3 days following application.
- In general, at temperatures above 28°C, moisten the plaster every 2 hours to prevent cracking.
- If applied indoors, ventilate the room as much as possible during the application and drying phases.
- When applied outdoors, in order to avoid prolonged exposure to adverse weather conditions, it is essential to proceed as follows:
 - after applying the last layer of *Diathonite Thermactive* and waiting for complete curing (not before 10-15 days), it is recommended to coat the plaster with the chosen skim coat.
 - Once the latter is completely cured (not before 7 days), apply the finish.

SANDED DIATHONITE

Carefully protect floors, window frames, and other elements using protective sheets or masking tape. To prepare the floors, use a single-disc floor machine

equipped with a diamond disc to remove irregularities and prepare the substrate.

On large wall surfaces, the use of a long-reach sander with a low-speed disc is recommended, such as the **LHS 2 225 EQI-Plus PLANEX** (Power: 400 W; eccentric motion¹; speed: 5,000 – 8,500 rpm; sanding stroke: 4.00 mm; backing pad diameter: 220.00 mm; abrasive diameter: 225.00 mm; length: 1.2/1.65 m; dust extraction connection Ø: 36/27 mm). During the process, proceed with uniform and light movements, avoiding concentrated pressure on a single point to prevent creating hollows. Any protrusions or excess material must be removed, periodically checking the flatness and regularity of the treated surface. To remove the most evident irregularities, initially use coarse-grained sandpaper (40-60 grit), then complete the operation with fine-grained sandpaper (80-120 grit) to achieve a surface that is perfectly smooth to the touch before the final coating. After sanding, carefully remove the dust produced using soft brushes or a professional vacuum cleaner, always ensuring adequate ventilation in indoor environments to promote the dispersion of volatile residues. As a final step, protect the surface by applying *Revela Color* (see technical data sheet), following the instructions in the relevant technical data sheet.

SMOOTHING AND FINISHING

For plaster smoothing, in both indoor and outdoor environments, it is possible to use the following finishing compounds: *Argatherm*, *Argatherm Ultrafine*, *Argatherm Color*, and *Argatherm Deco*. For application methods, drying times, and recommended thicknesses, please refer to the respective technical data sheets.

Outdoor Applications

For the finishing of skim coats in outdoor environments, use products such as *Decork Façade*, *Decork Mediterraneo*

¹ Eccentric movement

DIASEN

DIASEN SRL UNIPERSONALE – Società Benefit
Zona Industriale Berbentina 5 – 60041 Sassoferrato (AN) | Italy
+39 07329718 | diasen.com | P.IVA 01553210426
R.E.A. Ancona n. 150933 Reg. Imp. Ancona 01553210426
Cap. Soc. € 400.000,00 i.v.

The indications and requirements reported, although representing our best experience and knowledge, are to be considered indicative and must be confirmed by exhaustive practical applications. Diasen does not know the specificities of the processing and even less the determining characteristics of the application support. Therefore, before using the product, the applicator must in any case carry out preliminary tests, aimed at verifying the perfect suitability for the intended use and, in any case, assumes all responsibility that may derive from its use. In case of uncertainty and doubts, contact the company's technical office before starting the work, it being understood that such support constitutes a simple aid for the applicator, who must in any case guarantee the possession of adequate skills and experience for the installation of the product and for identifying the most suitable solutions. Always refer to the latest updated version of the technical data sheet, available on the website www.diasen.com, which cancels and replaces any other.

DIATHONITE THERMACTIVE

Cork and lime-based spray-applied thermal insulation

Fine, Decork Façade Reflex, Acrilid Protect Coating, or Plasterpaint (refer to technical data sheets), always ensuring the use of breathable and water-repellent finishes.

Indoor Applications

For indoor environments, the use of finishes such as *Decork Mediterraneo Fine, Decork Mediterraneo Deep, C.W.C. Stop Condense, or Limepaint* (refer to technical data sheets) is recommended, always prioritizing breathable products. In any case, it is advisable to refer to Diasen finishing systems.

FINISHING LAYERS

As with all plasters in the *Diathonite* range, *Diathonite Thermactive* must be reinforced with *Polites 140* fiberglass mesh when the installation of coatings such as tiles, stones, stoneware, or similar materials is planned, following the application methods described in the previous paragraphs. Subsequently, the surface must be finished with *Argatherm* finishing plaster, as indicated in its technical data sheet. To increase the system's resistance, *Argatherm* must be installed using *Polites 80* reinforcement mesh (refer to technical data sheet) with a sandwich system (*Argatherm + Polites 80 + Argatherm*). In wet areas, before laying the tiles, apply *WATstop* over *Argatherm*² following the instructions in the technical data sheet. It is recommended to observe a maximum interval of 24 hours between successive coats and to complete the application of the final layer within 48 hours. The maximum permitted weight for tiles is 45 kg/m².

SUGGESTIONS

- Do not apply with ambient and support temperatures lower than +5°C and higher than +30°C.

- During the summer season, apply the product during the coolest hours of the day, away from direct sunlight.
- Do not apply with imminent danger of rain or frost, in conditions of heavy fog or with relative humidity higher than 70%.
- Where deemed necessary, and only after contacting the Diasen technical office, it is possible to proceed with the application, by hand or by spray, of a first layer of *Diathonite Thermactive* as a rough-coat.
- It is recommended to waterproof and protect the points most subject to hygrometric stresses, such as at the base of the wall near the ground or in the joints between the flat roof slab and the external walls.
- If applied internally, it is essential that the external surface does not absorb water. Otherwise, treat the surface with *Revela Zero*.
- In case of application with *Diathonite Thermactive* left exposed, it is mandatory to protect the product with one of the *Revela* transparent protective coatings, depending on the area of application.
- In case of doubts regarding the consistency of the support and/or about any physical-chemical and mechanical incompatibilities between *Diathonite Thermactive* and the support, it is recommended to carry out an adhesion test identified and coordinated by the site management of the construction site in question.
- If the total thickness of the application exceeds 120 mm, it is necessary to provide for the insertion of at least two reinforcement meshes. The positioning of the meshes and the choice of the technical configuration must be confirmed by

² Argatherm helps control absorption and ensures more efficient coverage of WATstop.

DIASEN

DIASEN SRL UNIPERSONALE – Società Benefit
Zona Industriale Berbentina 5 – 60041 Sassoferrato (AN) | Italy
+39 07329718 | diasen.com | P.IVA 01553210426
R.E.A. Ancona n. 150933 Reg. Imp. Ancona 01553210426
Cap. Soc. € 400.000,00 i.v.

The indications and requirements reported, although representing our best experience and knowledge, are to be considered indicative and must be confirmed by exhaustive practical applications. Diasen does not know the specificities of the processing and even less the determining characteristics of the application support. Therefore, before using the product, the applicator must in any case carry out preliminary tests, aimed at verifying the perfect suitability for the intended use and, in any case, assumes all responsibility that may derive from its use. In case of uncertainty and doubts, contact the company's technical office before starting the work, it being understood that such support constitutes a simple aid for the applicator, who must in any case guarantee the possession of adequate skills and experience for the installation of the product and for identifying the most suitable solutions. Always refer to the latest updated version of the technical data sheet, available on the website www.diasen.com, which cancels and replaces any other.

DIATHONITE THERMACTIVE

Cork and lime-based spray-applied thermal insulation

the Site Management, also based on the assessment of structural movements and stresses of the support.

CLEANING

The equipment used can be washed with water before the product hardens.

SAFETY

While handling the product, use personal protective equipment and comply with the instructions provided in the product's Safety Data Sheet (SDS).



ISO 9001®
QUALITY



ISO 14001®
ENVIRONMENT



ISO 45001®
SAFETY

DIASEN

DIASEN SRL UNIPERSONALE – Società Benefit
Zona Industriale Berbentina 5 – 60041 Sassoferrato (AN) | Italy
+39 07329718 | diasen.com | P.IVA 01553210426
R.E.A. Ancona n. 150933 Reg. Imp. Ancona 01553210426
Cap. Soc. € 400.000,00 i.v.

The indications and requirements reported, although representing our best experience and knowledge, are to be considered indicative and must be confirmed by exhaustive practical applications. Diasen does not know the specificities of the processing and even less the determining characteristics of the application support. Therefore, before using the product, the applicator must in any case carry out preliminary tests, aimed at verifying the perfect suitability for the intended use and, in any case, assumes all responsibility that may derive from its use. In case of uncertainty and doubts, contact the company's technical office before starting the work, it being understood that such support constitutes a simple aid for the applicator, who must in any case guarantee the possession of adequate skills and experience for the installation of the product and for identifying the most suitable solutions. Always refer to the latest updated version of the technical data sheet, available on the website www.diasen.com, which cancels and replaces any other.

DIATHONITE THERMACTIVE

Cork and lime-based spray-applied thermal insulation

TECHNICAL SPECIFICATIONS

* The reported data, although obtained by carrying out standardized test methodologies, are indicative and may undergo changes as the specific construction site conditions vary.

PHYSICAL / TECHNICAL DATA*		
TECHNICAL DATA	VALUE	UNIT OF MEASUREMENT
Yield	2.60 (± 20%) <i>for each cm of thickness</i>	kg/m ²
	1.35 (± 20%) <i>per inch of thickness</i>	lb/ft ²
Aspect	powder	-
Color	Light grey	-
Density	250 ± 15%	kg/m ³
	15.67 ± 15 %	lb/ft ³
Grain size	0 – 3	mm
	0 – 0.12	in
Water to add to the mixture	0,8 – 1,0 <i>12 – 15 L for each 15 kg bag</i>	L/kg
	0.096 – 0.120 gal (US) <i>per paper bag (33.07 lb)</i>	gal (US) / lb
Minimum thickness	15 / 0.6	mm / inches
Maximum thickness per coat	40 / 1.6	mm / inches
Minimum thickness <i>for ceiling applications</i>	20 / 0.8	mm / inches
Maximum thickness <i>for ceiling applications</i>	40 / 1.6	mm / inches
Application temperature	+5 / +30	°C
	+41 / +95	°F
Workability time (UNI EN 1015-9 – method B)	40	min
Drying time (T=23°C; U.R. 50%)	15	days
Storage	12	months
Packaging	Paper bag 15 kg	kg

PERFORMANCES*				
FINAL PERFORMANCES	VALUE	UNIT	STANDARDS	RESULTS
Thermal conductivity ($\lambda_{10, dry}$)	0,035	W/mK	UNI EN 12667 ASTM C518	category T1
Thermal resistance (R) <i>per 1 cm of thickness</i>	0,285	m ² K/W	UNI 10355 ASTM C518	-
Specific heat capacity (c)	1000	J/kg K	UNI EN 1745 UNI EN 10456	-
	0,239	kcal/kg °C	-	
Thermal diffusivity (α)	0,148 x 10 ⁻⁶	m ² /s	UNI TS 11300-1	-
Vapour permeability coefficient (μ)	3	-	UNI EN ISO 12572	highly breathable
Compressive strength	2,80	N/mm ²	EN 998-1	category CS II
	406.1	lbf/in ² (psi)	EN 998-2	M2,5
Flexural strength	1,00	N/mm ²	UNI EN 1015-11	-
	145.0	lbf/in ² (psi)		

DIASEN


DIASEN SRL UNIPERSONALE – Società Benefit
Zona Industriale Berbentina 5 – 60041 Sassoferrato (AN) | Italy
+39 07329718 | diasen.com | P.IVA 01553210426
R.E.A. Ancona n. 150933 Reg. Imp. Ancona 01553210426
Cap. Soc. € 400.000,00 i.v.

The indications and requirements reported, although representing our best experience and knowledge, are to be considered indicative and must be confirmed by exhaustive practical applications. Diasen does not know the specificities of the processing and even less the determining characteristics of the application support. Therefore, before using the product, the applicator must in any case carry out preliminary tests, aimed at verifying the perfect suitability for the intended use and, in any case, assumes all responsibility that may derive from its use. In case of uncertainty and doubts, contact the company's technical office before starting the work, it being understood that such support constitutes a simple aid for the applicator, who must in any case guarantee the possession of adequate skills and experience for the installation of the product and for identifying the most suitable solutions. Always refer to the latest updated version of the technical data sheet, available on the website www.diasen.com, which cancels and replaces any other.

DIATHONITE THERMACTIVE

Cork and lime-based spray-applied thermal insulation

Dried mortar porosity	71%	-	ISO 15901-1	-
Total pores volume	1372	mm ³ /g	-	-
Reaction to fire	class A1	-	UNI EN 13501-1	-

INDOOR AIR QUALITY (IAQ) CERTIFICATION		
Evaluation of the results		
Regulation or protocol	Version of regulation or protocol	Conclusion
<i>French VOC Regulation</i>	Decree of March 2011 (DEVL1101903D) and Arrêté of April 2011 (DEVL1104875A) modified in February 2012 (DEVL1133129A)	
<i>French CMR components</i>	Regulation of April and May 2009 (DEVP0908633A and DEVP0910046A)	Pass
<i>Italian CAM Edilizia</i>	Decree 11 October 2017 (GU n.259 del 6-11-2017)	Pass
<i>AgBB/ABG</i>	Anforderungen an bauliche Anlagen bezüglich des Gesundheitsschutzes, ABG May 2019, AgBB August 2018	Pass
<i>Belgian Regulation</i>	Royal decree of May 2014 (C-2014/24239)	Pass
<i>Indoor Air Comfort®</i>	Indoor Air Comfort 7.0 of May 2020	Pass
<i>Blue Angel (DE-UZ 113)</i>	DE-UZ 113 for "Low-Emission Floor Covering Adhesives and other Installation Materials" (Version January 2019)	Pass
<i>BREEAM International</i>	BREEAM International New Construction v2.0 (2016)	Exemplary Level
<i>BREEAM® NOR</i>	BREEAM-NOR New Construction v1.2 (2019)	Pass
<i>LEED®</i>	"Low-Emitting Material" according to the requirements of LEED v4.1	Pass
<i>CDPH: Classroom scenario</i>	CDPH/EHLB/Standard Method V1.2. (January 2017)	Pass

DIASEN

DIASEN SRL UNIPERSONALE – Società Benefit
 Zona Industriale Berbentina 5 – 60041 Sassoferrato (AN) | Italy
 +39 07329718 | diasen.com | P.IVA 01553210426
 R.E.A. Ancona n. 150933 Reg. Imp. Ancona 01553210426
 Cap. Soc. € 400.000,00 i.v.

The indications and requirements reported, although representing our best experience and knowledge, are to be considered indicative and must be confirmed by exhaustive practical applications. Diasen does not know the specificities of the processing and even less the determining characteristics of the application support. Therefore, before using the product, the applicator must in any case carry out preliminary tests, aimed at verifying the perfect suitability for the intended use and, in any case, assumes all responsibility that may derive from its use. In case of uncertainty and doubts, contact the company's technical office before starting the work, it being understood that such support constitutes a simple aid for the applicator, who must in any case guarantee the possession of adequate skills and experience for the installation of the product and for identifying the most suitable solutions. Always refer to the latest updated version of the technical data sheet, available on the website www.diasen.com, which cancels and replaces any other.